

Corrosion-Resistant Titanium Alloys

Allegheny Ludlum Corporation, a division of Allegheny Teledyne Incorporated, offers corrosion-resistant titanium alloys produced as plate, sheet, and strip products. Titanium's low density and high strength-to-weight ratio make it the material of choice for many corrosive chemical environments, including oxidizing chloride solutions (including seawater) and chlorine-based bleaches.

Product Grades, Forms and Requirements*

Grade	Nominal Composition	Forms		
		Coil	Sheet	Plate
Grade 1	Ti	X	X	X
Grade 2	Ti	X	X	X
Grade 3	Ti	X	X	X
Grade 4	Ti	X	X	X
Grade 5	Ti-6 Al-4V			X
Grade 7	Ti (Gr2) 0.2 Pd	X	X	X
Grade 9	Ti-3 Al-2.5V	X	X	**
Grade 11	Ti (Gr1) 0.2 Pd	X	X	**
Grade 12	Ti-0.3Mo-0.8Ni	X	X	X
Grade 16	Ti (Gr2) 0.05 Pd	X	X	**
Grade 17	Ti (Gr1) 0.05 Pd	X	X	**
Grade 18	Ti (Gr9) 0.05 Pd	X	X	**

*Produced to ASTM, AMS, ASME and MIL Specifications.

**Inquire with your sales representative.

Sizes, Tolerances*

Sheet	
Width** (in)	Thickness (in)
24" - 48"	Up to 0.1874"
Strip	
0.250" - 24"	0.001" - 0.1874"
Plate	
96"	0.1875" - 4.0" x 360" max

* Tolerances per relevant ASTM, AMS, ASME and MIL Requirements; available sizes are grade and gage dependent.

**Typically supplied with #3 EDGE on coil product.

Finish varies depending upon size. Consult your sales representative with your specific finish requirements.

TYPICAL APPLICATIONS

Heat Transfer

A major industrial application for titanium is in heat transfer applications for which the cooling medium is seawater, brackish water or polluted water. Titanium condensers, shell and tube heat exchangers, and plate and frame heat exchangers are used extensively in power plants, refineries, air conditioning systems, chemical plants, offshore platforms, surface ships and submarines.

Millions of feet of welded titanium tubing are in power plant condenser service, and there have been no reported failures due to corrosion on the cooling water side.

DSA-Dimensional Stable Anodes

The unique electrochemical properties of the titanium DSA make it the most energy efficient unit for the production of chlorine, chlorate and hypochlorite.

Desalination

Its excellent resistance to corrosion, erosion, and high condensation efficiency make titanium the cost-effective and dependable material for critical segments of desalination plants. Increased usage of very thin walled welded tubing makes titanium competitive with copper-nickel.

Extraction and Electro-Winning of Metals

Hydrometallurgical extraction of metals from ores in titanium reactors is an environmentally friendly alternative to smelting processes. Extended lifespan, increased energy efficiency, and greater product purity are factors promoting the usage of titanium electrodes in electro-winning and electro-refining of metals like copper, gold, manganese and manganese dioxide.

Medical

Titanium is widely used for implants, surgical devices, pacemaker cases and centrifuges. Titanium is the most biocompatible of all metals due to its resistance to attack by body fluids, its high strength and its low modulus.

Hydrocarbon Processing

The need for longer equipment life, coupled with requirements for less downtime and maintenance, favor the use of titanium in heat exchangers, vessels, columns and piping systems in refineries, LNG plants and offshore platforms. Titanium is immune to general attack and stress corrosion cracking by hydrocarbons, hydrogen sulfide, brines and carbon dioxide.

Marine Applications

Because of high toughness, high strength and exceptional erosion/corrosion resistance, titanium is cur-

rently being used for submarine ball valves, fire pumps, heat exchangers, castings, hull material for deep sea submersibles, water jet propulsion systems, shipboard cooling and piping systems.

Chemical Processing

Titanium vessels, heat exchangers, tanks, agitators, coolers, and piping systems are utilized in the processing of aggressive compounds, like nitric acid, organic acids, chlorine dioxide, inhibited reducing acids and hydrogen sulfide.

Architectural Applications

Titanium's use as an architectural material is rapidly gaining world wide acceptance. Its corrosion resistance, light weight, strength, durability, soft metallic appearance, and almost unlimited life span give titanium a cost effective edge over other materials. Typical areas include roofs, ceilings, exterior wall panels, sculptures and monuments.

CORROSION RESISTANCE

General Corrosion

Allegheny Ludlum titanium alloys have excellent resistance to corrosion in a wide variety of environments including seawater, salt brines, inorganic salts, bleaches, wet chlorine, alkaline solutions, oxidizing acids, and organic acids. Titanium is incompatible with fluorides, strong reducing acids, very strong caustic solutions, and anhydrous chlorine. Due to its combustibility, titanium is not suitable for pure oxygen service. Titanium does not release any toxic ions into aqueous solutions, thus helping to prevent pollution.

Crevice Corrosion

Allegheny Ludlum titanium alloys have excellent resistance to crevice corrosion in salt solutions and generally outperforms stainless steels. Unalloyed titanium (grades 1, 2, 3, and 4) typically do not suffer crevice corrosion at temperatures below 80°C (175°F) at any pH.

Palladium alloyed CP titanium (grades 7, 11, 16 and 17) are more resistant and typically do not suffer crevice corrosion at temperatures below 250°C (480°F) at pH greater than 1.

Microbiologically Influenced Corrosion (MIC)

Titanium alloys appear to be immune to MIC. They do suffer biofouling, but this can be controlled by chlorination (which does not impair titanium).

Galvanic Corrosion

Although it is a reactive metal, due to the extreme stability of the passive film which forms on its surface, titanium typically exhibits noble behavior. Thus it functions as the cathode when coupled with other metals. Titanium is not affected by galvanic corrosion, but can accelerate corrosion of other metals.

Stress Corrosion Cracking

Allegheny Ludlum titanium alloys have excellent resistance to stress corrosion cracking in hot chloride salt solutions.

Erosion Corrosion

Titanium alloys exhibit excellent resistance to flow-induced and erosion corrosion at velocities to above 40 m/sec.

Hydrogen Embrittlement

Titanium alloys are susceptible to hydrogen embrittlement under some circumstances. This is generally less of a problem for the low-strength grade 1 and grade 2 titanium alloys than for higher strength titanium alloys. Absorption of hydrogen by titanium normally occurs when the temperature is above 80°C (175°F), and the titanium is galvanically coupled to an active metal or an impressed current or the pH is less than 3 or greater than 12.

FABRICATION

Welding

Allegheny Ludlum CP titanium alloys are readily weldable using GTAW (gas tungsten arc welding) or TIG (tungsten inert gas) processes if adequate shielding is provided using pure inert gas (argon or helium). Use of a trailing shield is recommended. Titanium must be free of oil, grease or other contamination before welding. Preheat or postheat are not required. Friction welding, laser welding, resistance welding, plasma arc welding, electron beam welding, and diffusion bonding can also be used.

Formability

Allegheny Ludlum titanium is readily formed at room temperature, using techniques and equipment suitable for steel. When correct parameters have been established, tolerances similar to those attainable with stainless steel are possible with titanium and its alloys. Three factors make forming of titanium somewhat different from forming of other metals.

1. The room temperature ductility of titanium, as measured by uniform elongation, may be less than that of other common structural metals. This means that titanium may require more generous bend radii and has lower stretch formability.
2. The modulus of elasticity of titanium is about half that of steel. This causes significant spring back after forming titanium for which compensation must be made.
3. The galling tendency of titanium is greater than that of stainless steel. This necessitates close attention to lubrication in any forming operation in which titanium is in contact (particularly moving contact) with metal dies or other forming equipment.

The various grades of Allegheny Ludlum titanium exhibit differences in formability. Grades 1, 11 and 17 titanium, which are the softest and most ductile grades, exhibit the greatest formability. The slightly greater strengths of Grades 2, 7 and 16 titanium are still quite formable, but less so than Grades 1, 11 or 17. The higher strength of Grade 4 titanium makes it the least formable of the CP titanium alloys.

Normally, titanium surfaces are acceptable for forming operations as received from the mill. Gouges and other surface marks introduced during handling should be removed by sanding. To prevent edge cracking, burred and sharp edges should be filed smooth before forming.

Data are nominal and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those shown herein.

Chemical Composition (Nominal %)

Grade	Carbon Max	Oxygen Max	Nitrogen Max	Iron Max	Al	V	Pd	Mo	Ni	Hydrogen Max
Grade 1	0.08	0.18	0.03	0.2						0.015
Grade 2	0.08	0.25	0.03	0.3						0.015
Grade 3	0.08	0.35	0.05	0.3						0.015
Grade 4	0.08	0.40	0.05	0.5						0.015
Grade 5	0.08	0.20	0.05	0.4	6	4				0.015
Grade 7	0.08	0.25	0.03	0.3			0.20			0.015
Grade 9	0.05	0.12	0.02	0.25	3	2.5				0.015
Grade 11	0.08	0.18	0.03	0.2			0.20			0.015
Grade 12	0.08	0.25	0.03	0.3				0.3	0.8	0.015
Grade 16	0.08	0.25	0.03	0.3			0.05			0.015
Grade 17	0.08	0.18	0.03	0.2			0.05			0.015
Grade 18	0.05	0.15	0.03	0.25	3	2.5	0.05			0.015

Typical Mechanical Properties*

Grade	Tensile KSI Min	Yield KSI Min/Max	% Elongation/2" Min
Grade 1	35	25/45	24
Grade 2	50	40/65	20
Grade 3	64	55/75	18
Grade 4	80	70/95	15
Grade 5	130	120**	10
Grade 7	50	40/65	20
Grade 9	90	70**	15
Grade 11	35	25/45	24
Grade 12	70	50**	12
Grade 16	50	40/65	20
Grade 17	35	25/45	24
Grade 18	90	70**	15

*Mill Annealed Condition

**Minimum

Typical Physical Properties

	Grade 1, 2, 3, 4, 7, 11, 12, 16, 17, 18	Grade 5	Grade 9
Density	0.163 lb/in ³	0.160 lb/in ³	0.162 lb/in ³
Modulus	15 x 10 ⁶ psi	16 x 10 ⁶ psi	15 x 10 ⁶ psi
Beta Transus (± 25°F)	1635F - 1735°F	1800°F	1715°F
Thermal Conductivity	13-10 Btu/ft•h•°F	4 Btu/ft•h•°F	10 Btu/ft•h•°F
Thermal Expansion (32-600°F)	5.1 x 10 ⁻⁶ /°F	5.3 x 10 ⁻⁶ /°F	5.5 x 10 ⁻⁶ /°F
Melt Temperature	~3000°F	~3000°F	~3000°F

Data are nominal and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those shown herein.

Technical DATA SHEET

Allegheny Ludlum's staff of research and development engineers and mill product metallurgists welcome the opportunity to discuss your technical requirements during the design and specification stage. To access this technical assistance, please call:

(724) 226-6300

*For expedient handling of your sales inquiry,
please contact one of the following sales offices:*

ALLEGHENY LUDLUM SALES OFFICES

Sheet

Stainless, High Tech Alloy & Titanium

800-A-LUDLUM (800-258-3586)

(FAX) 412-252-3162

Standard Strip & Foil

Stainless, High Tech Alloy

800-777-2822

(FAX) 724-845-0691

Plate Mill Plate & Continuous Mill Plate

Stainless, High Tech Alloy & Titanium

800-289-7528

(FAX) 724-229-3775

Precision Rolled Strip® & Titanium Foil

The Allegheny Rodney Strip Division

Stainless & High Tech Alloys

800-225-8104

(FAX) 508-993-3176

Tool Steels

800-521-2696

(FAX) 724-229-3770

Silicon Steel

800-289-7454

(FAX) 724-845-0696



Dedicated to Quality Specialty Steel®

© Registered Trademark of ATI Properties, Inc.